



Test Report


Fungi Resistance Measurement According to ASTM C1338 on Lewco HFB Fiberglass Blanket Supplied by Lewco Specialty Products, Inc.

Prepared For:

Mr. Peter Zhou
Lewco Specialty Products, Inc.
6859 Renoir Avenue
Baton Rouge, LA 70806

R & D Services, Inc.
P.O. Box 2400
Cookeville, Tennessee 38502-2400

Report: RD16519


Stuart Ruis
President

September 1, 2016

The test results in this report apply only to the specimens tested. The tests conform to the respective test methods except for the report requirements. The report includes summary data but a full complement of data is available upon request. This report shall not be reproduced, except in full, without written approval of R & D Services, Inc. This report must not be used by the client to claim product endorsement by R & D Services, Inc., IAS or any other organization.



P.O. Box 2400
Cookeville, Tennessee 38502-2400
Phone: 931-372-8871
Fax: 931-525-3896

Fungi Resistance Test Report

Test Number: RD161570FR

Date of Test: August 1 - 29, 2016

Specimen Number: 1916160729-8

Date of Manufacture: Unknown

Description of Test Specimen: Lewco HFB Fiberglass Blanket

Test Method: ASTM C 1338-14, "Standard Test Method for Determining Fungi Resistance of Insulating Materials and Facings."

Report Prepared For: Lewco Specialty Products, Inc. / Mr. Peter Zhou

Test specimens and comparative material are exposed to a 28 day inoculation period. After the inoculation period the specimens are removed from test chamber and evaluated under 40X magnification. Each of the test specimens are determined to have no fungal growth, fungal growth no greater than the comparative material, or fungal growth greater than the comparative material.

<u>Specimen</u>	<u>Fungal Growth Comparison</u>
1	No growth.
2	No growth.
3	No growth.

Comparative Material: Birch

The pass/fail result: Pass

Basis for the pass/fail result: Three of three specimens passed.

Carla King
Evaluation:

9/1/16
Date:

Shawn King
Review:

9/1/16
Date: